

HI-PRO (IP-72021) OUTRIGGER PAD

Our Hi-Pro outrigger pads offer complete protection when working on high value flooring with their non-marking rubber base. They are also hi-viz yellow for working in pedestrianised areas.

- Engineered from High Density Polyethylene (HDPE)
- Non-marking rubber base
- Tough and stable support for outrigger legs
- Resistant to water, oil and chemicals
- Lightweight and easy to handle

SUITABLE FOR:













	TEST METHOD	TEST RESULTS
PROPERTIES Physical Properties	TEST WETTOD	TEST NESOLIS
Density	ASTM D-792	0.937-0.98 g/cm ³
Water Absorption	ASTM D-570(2)	<0.01%
Jpper Temperature Limit	-	90°C
_ower Temperature Limit	-	-269°C
Mechanical Properties		
Tensile Strength at Yield	ASTM D-638	>17 MPa
Tensile Strength at Break	ASTM D-638	>35 MPa
Elongation at Yield	ASTM D-638	12%
Ultimate Elongation	ASTM D-638 / ISO527	>350% / >400 %
Tensile Modulus	ASTM D-638	820 MPa
zod impact, Notched	ASTM D-256 Type A	No break KJ/m²
Flexural Strength	ASTM D-790	26 MPa
Flexural Modulus	ASTM D-790	760 MPa
Compression Strength (10%Def)	ASTM D-695	27 MPa
Compressive Modulus	ASTM D-695	550 MPa
Hardens (Shore D Hardness)	ASTM D-2240	60-70 Shore D
Static Friction Coefficient	ASTM D-1894	0.11-0.17
Dynamix Friction Coefficient	ASTM D-1894	0.7-0.11
Thermal Properties		
Coefficient of Linear Expansion	ASTM D-696	1.5 10 ⁻⁴ /°C
Thermal Conductivity @23'C	ASTM D-177	0.4W/m.k
Specific Heat @ 23'C	ASTM E-1269	0.48 Cal/g°C
Electrical Properties		

Product Code: IP-72021

Dimensions (mm): 400 x 400 x 30

Load Capacity (tonnes): 8.00

Weight (kgs): 4.40

Recess Size (mm): 300 x 8

Material: **HDPE**



The data mentioned in this brochure are average values ascertained by current statistical returns and tests, but we cannot accept any responsibility for their accuracy.

ASTM D-150



Dielectric Constant @1MHZ





BE CONFIDENT. BUY QUALITY.

