

ECO LIFT Material Specifications (HMW-PE)

Properties	Unit	Test method	Test Result
Density	g/cm ³	ASTM D1505	0.93-0.955
Melting Point	°C	ASTM D-3418	133-135
Tensile Strength at Break	MPa	ISO 527:2012	14-16
Tensile Strength at Yield	MPa	ISO 527:2012	23-26
Elasticity Modulus	MPa	ISO 527:2012	1100-1210
Elongation at Break	%	ISO 527:2012	80-100
Charpy Impact Strength-Notched	KJ/m ²	ISO179-1:2011	33-37
Hardness	Shore D	ISO868:2003	67-69
Wear Resistance Sand-Slurry-Test	%	ISO15527	372
Average Coefficient of Linear Thermal Expansion	m/(m/k)		2x10 ⁻⁴
Service Temperature	°C	-	-100 to +80

Note: 1g/cm³ = 1,000 kg/ m³; 1Mpa = 1N/mm²; 1kV/mm = 1MV/m

The data mentioned in this brochure are average values ascertained by current statistical returns and tests, but we cannot accept any responsibility for their accuracy.



TECHNICAL
ADVICE



EASY
ORDERING



NEXT DAY
DELIVERY
Order by 4pm

BE CONFIDENT. BUY QUALITY.

